

Partial Translation of Appendix 4

Product Name: Cu-At-200 (the copper powder used in Examples 3 and 6 of Reference 1)

Particle Size Distribution (%): 5.0 or less

Reference Values

Product Name: Bra-At-200 (the brass powder used in Examples 1 and 4 of Reference 1)

Particle Size Distribution (%): 3.0 or less

Reference Values

## Appendix 4

3/3

品 名		Cu-Al-200
顧客名		一般
見掛け密度 (g/cm <sup>3</sup> )		4.10 ~ 5.10
流動度 (s/50g)		—
粒度分布 (%)	+ 150 $\mu$ m	—
	+ 100 $\mu$ m	—
	+ 75 $\mu$ m	5.0 以下
	+ 63 $\mu$ m	} 参考値
	+ 45 $\mu$ m	
	— 45 $\mu$ m	45.0 ~ 85.0
その他の検査項目		
仕様書文書番号		—
商品コード		042400
製品規格番号		27-002

品 名		Brz-Al-200
顧客名		一般
見掛け密度 (g/cm <sup>3</sup> )		2.80 ~ 3.40
流動度 (s/50g)		参考値
粒度分布 (%)	+ 150 $\mu$ m	—
	+ 75 $\mu$ m	3.0 以下
	+ 63 $\mu$ m	} 参考値
	+ 45 $\mu$ m	
	— 45 $\mu$ m	70.0 ~ 95.0
	20 (%)	27.0 ~ 33.0
その他の検査項目		
仕様書文書番号		
商品コード		043800
製品規格番号		22-033